

Requested document:	JP11315109 click here to view the pdf document
---------------------	--

CATALYST FOR POLYMERIZING OLEFIN, TRANSITION METAL COMPOUND, POLYMERIZATION OF OLEFIN AND ALPHA-OLEFIN-CONJUGATED DIENE COPOLYMER

Patent Number: JP11315109

Publication date: 1999-11-16

Inventor(s): FUJITA TERUNORI;; DOI YASUSHI;; MITANI MAKOTO;; MATSUI NARIKAZU;; SAITO JUNJI;; NITAHARA MASATOSHI;; SUGI KIYOAKI;; MAKIO HARUYUKI;; TSUTSUI TOSHIYUKI

Applicant(s): MITSUI CHEM INC

Requested Patent: ☐ [JP11315109](#)

Application Number: JP19980132706 19980427

Priority Number (s):

IPC Classification: C08F4/642; C08F10/00

EC Classification:

Equivalents:

Abstract

PROBLEM TO BE SOLVED: To obtain the subject catalyst capable of providing an α -olefin-conjugated diene copolymer having excellent olefin polymerization activity, a narrow distribution of molecular weight and scarcely containing a cyclopentane skeleton in the polymer chain by using a specific transition metal compound.

SOLUTION: This catalyst comprises (A) a transition metal compound represented by the formula [M is a group 3 to 11 transition metal; (m) is 1-6; R<1> to R<6> are each H, a halogen or the like; (n) is a number satisfying the valence of M; X is H, a hydrocarbon or the like] and (B) a compound selected from an organometallic compound, an organoaluminumoxy compound and a compound reactive with the component A and forming an ion pair. Compounds, or the like, in which M is a group 4 or 5 transition metal; (m) is 1-3; R<1> is a hydrocarbon; R<2> to R<5> are each H; R<6> and X are each a halogen are new compounds in the compound represented by the formula. The compound represented by the formula is obtained by reacting, e.g. salicylaldehydes with a primary amine compound represented by the formula R<1>-NH₂ and then reacting the produced ligand with a transition metal-containing compound.

Data supplied from the esp@cenet database - I2